

cl
as inventor, and which is now U.S. Patent No. 6,030,423, which issued February 29, 2000,
the disclosure of which is incorporated by reference.--.

In the Claims

Please replace the claims with the following clean version of the entire set of pending claims, in accordance with 37 C.F.R. § 1.121(c)(1)(I).

A marked up version showing amendments to any claims being changed is provided in one or more accompanying pages separate from this amendment in accordance with 37 C.F.R. § 1.121(c)(1)(ii).

1. Canceled.
2. Canceled.
3. Canceled.
4. Canceled.
5. Canceled.
6. Canceled.
7. Canceled.
8. Canceled.

9. (Amended) A method of conductively interconnecting electronic components comprising:
- providing a curable adhesive composition comprising an epoxy terminated silane comprising a glycidoxy methoxy silane;
- Sub 7
-

providing first and second electronic components to be conductively connected with one another;

interposing the curable adhesive composition between the first and second electronic components; and

curing the adhesive into an electrically conductive bond electrically interconnecting the first and second components.

10. The method of claim 9 wherein at least one of the components comprises a nickel containing metal surface over which the curable adhesive composition is received.

11. ~~Cancel.~~

12. The method of claim 9 wherein the epoxy terminated silane comprises a glycidoxypropyltrimethoxysilane.

13. The method of claim 9 wherein the epoxy terminated silane is present in the curable adhesive composition at less than or equal to about 2% by weight.

14. The method of claim 9 wherein the epoxy terminated silane is present in the curable adhesive composition at less than or equal to about 1% by weight.

15. Canceled.
16. Canceled.
17. Canceled.
18. Canceled.
19. Canceled.
20. Canceled.
21. Canceled.
22. Canceled.

23. A method of conductively interconnecting electronic components comprising:
interposing a curable epoxy composition between first and second electrically
conductive components to be electrically interconnected, at least one of the components
comprising a metal surface with which the curable epoxy is to electrically connect; and
curing the epoxy into an electrically conductive bond electrically interconnecting the
first and second components, the epoxy having an effective metal surface wetting
concentration of silane to form a cured electrical interconnection having a contact
resistance through said metal surface of less than or equal to about 0.3 ohm-cm².

24. The method of claim 23 wherein the epoxy has an effective metal surface
wetting concentration of silane to form a cured electrical interconnection having a
resistance through said metal surface of less than or equal to about 0.16 ohm-cm².

25. The method of claim 23 wherein the epoxy has an effective metal surface wetting concentration of silane to form a cured electrical interconnection having a resistance through said metal surface of less than or equal to about 0.032 ohm- cm².

26. The method of claim 23 wherein the metal surface wetting concentration of silane in the curable adhesive composition is less than or equal to about 2% by weight.

27. The method of claim 23 wherein the metal surface wetting concentration of silane in the curable adhesive composition is less than or equal to about 1% by weight.

28. The method of claim 23 wherein the metal surface comprises nickel over which the curable adhesive composition is received.

- 50b
F117
- 29. Canceled.
 - 30. Canceled.
 - 31. Canceled.
 - 32. Canceled.
 - 33. Canceled.
 - 34. Canceled.
 - 35. Canceled.
 - 36. Canceled.
 - 37. Canceled.
 - 38. Canceled.
 - 39. Canceled.

Appl. No. 09/480,076

- 40. Canceled.
- 41. Canceled.
- 42. Canceled.
- 43. Canceled.
- 44. Canceled.
- 45. Canceled.
- 46. Canceled.
- 47. Canceled.
- 48. Canceled.
- 49. Canceled.
- 50. Canceled.

540
4/1